

- Sub
B7
- (b) providing a balance weight;
- (c) providing an adhesive material between the unbalanced driveshaft and the balance weight;
- (d) moving the unbalanced driveshaft and the balance weight toward one another such that a first portion of the adhesive material is disposed between the unbalanced driveshaft and the balance weight at a location for balancing the driveshaft for rotation about an axis and a second portion of the adhesive material extends from between the unbalanced driveshaft and the balance weight; and
- (e) exposing the second portion of the adhesive material to an accelerated curing process to cure the second portion of the adhesive material, thereby retaining the balance weight on the driveshaft, prior to curing the first portion of the adhesive material.
- A

15. The method defined in Claim 14 wherein the balance weight is formed having a serrated outer peripheral surface, and wherein the second portion of the adhesive material extends between the unbalanced driveshaft and the serrated outer peripheral surface of the balance weight.

16. The method defined in Claim 14 wherein the balance weight is formed having a relatively thin rim portion, and wherein the second portion of the adhesive material extends between the unbalanced driveshaft and the relatively thin rim portion of the balance weight.

17. The method defined in Claim 14 wherein the balance weight is formed having a relatively thin rim portion and a serrated outer peripheral surface, and wherein the second portion of the adhesive material extends between the unbalanced driveshaft and the serrated outer peripheral surface of the relatively thin rim portion of the balance weight.

18. The method defined in Claim 14 wherein the unbalanced driveshaft has an outer surface defining a shape, and wherein the balance weight has an inner surface defining a shape that corresponds to the outer surface of the unbalanced driveshaft.

19. The method defined in Claim 14 wherein the unbalanced driveshaft and the balance weight are pressed against one another such that the first portion of the adhesive material is disposed between the unbalanced driveshaft and the balance weight and the second portion of the adhesive material is extruded outwardly from between the unbalanced driveshaft and the balance weight such that the second portion of the adhesive material extends from between the unbalanced driveshaft and the balance weight.

20. The method defined in Claim 14 wherein the accelerated curing process is ultraviolet radiation.

21. The method defined in Claim 14 wherein the accelerated curing process is heat.

22. The method defined in Claim 14 wherein the adhesive material includes an activator part that is applied to one of the unbalanced driveshaft and the balance weight and an adhesive part that is applied to the other of the unbalanced driveshaft and the balance weight.

23. The method defined in Claim 14 wherein the unbalanced driveshaft has an outer surface, the balance weight has an inner surface disposed adjacent to the outer surface of the unbalanced driveshaft, the balance weight has an outer surface opposite the inner surface, and the second portion of the adhesive material extends from between the unbalanced driveshaft and the outer surface of the balance weight.